

RENOLIN B RANGE

High quality AW hydraulic & lubricating oils

Description

The RENOLIN B series is based on selected mineral base oils. High-quality additives improve the ageing and oxidation stability. They also guarantee excellent corrosion protection properties (steel and iron materials). Synergistically acting copper deactivators protect copper / yellow metal materials. The selected Anti-Wear- / mild EP-additives based on zincdialkyldithiophosphates protect hydraulic pumps, motors, components and machine elements from wear (at low and high temperatures and at high loads). The RENOLIN B oils are mineral oil-based hydraulic fluids according to DIN 51524-2 (demulsifying, zinc-containing) and lubricating oils according to DIN 51517.

Application

Universally applicable demulsifying hydraulic fluids and lubricating oils. They can be used in all types of mobile and stationary hydraulic units where the use of a demulsifying hydraulic oil (type HLP) is recommended.

Synergistically acting additives guarantee a long lifetime and the highest hydraulic performance. Even at high temperatures and high loads the base oils together with the additives ensure that the system will be operated reliably during a long lifetime.

Advantages/Benefits

- Excellent demulsibility
- Very good corrosion protection to steel
- Good corrosion protection to copper
- High ageing stability / high oxidation stability
- Good AW wear protection
- Very good hydrolytic stability
- Excellent filtration behaviour (dry, wet)
- Low foaming
- Excellent air release

Application

The RENOLIN B RANGE fulfils the high requirements of the DENISON HF 0 specification (hybrid pump test, a combination of a vane and a piston pump - T6H20C combination).

The RENOLIN B oils offer an excellent thermal stability (Cincinnati Milacron B – pass). The formation of hydrolysis products - when water enters the hydraulic system - will be avoided. The RENOLIN B series shows an excellent filtration behaviour. Under dry as well as wet conditions, the filtration behaviour is excellent (low pressure, good flowability).

Specifications

The RENOLIN B RANGE products fulfil and surpass the requirements according to:

- DIN 51524-2: HLP
- ISO 6743-4: HM
- Denison HF 1, HF 2, HF 0
- Vickers I 286-S, M 2950-S
- Cincinnati Machine P68, P69, P70
- US Steel 127, 136

Well known pump manufacturers have approved the RENOLIN B RANGE oils, for example:

- Denison
- Bosch Rexroth
- Sauer Danfoss

CHARACTERISTICS: RENOLIN B RANGE

RENOLIN		B 1 VG 5	B 3 VG 10	B 4 VG 15	B 5 VG 22	B 10 VG 32	
Characteristics	Unit						Test Method
ISO VG		5	10	15	22	32	DIN 51519
Kinematic viscosity							DIN EN ISO 3104
at 40°C	mm ² /s	5	10	15	22	32	
at 100°C	mm ² /s	1.7	2.6	3.2	4.4	5.5	
Viscosity Index		-	95	90	107	109	DIN ISO 2909
Density at 15°C	kg/m ³	837	850	865	863	876	DIN 51757
Colour	ASTM	0.5	0.5	0.5	0.5	0.5	DIN ISO 2049
Flashpoint (Cleveland Open Cup) °C		130	178	150	200	205	DIN ISO 2592
Auto-ignition temperature °C		-	320	-	330	345	DIN 51794
Pour point °C		-20	-42	-42	-27	-24	DIN ISO 3016
Neutralisation number	mg KOH/g	0.5	0.5	0.5	0.5	0.5	DIN 51558-3
Air release at 50°C (max.)	minutes	1	1	2	3	4	DIN ISO 9120
Demulsification							DIN ISO 6614
at 54°C	minutes	10	10	10	10	10	
at 82°C	minutes	-	-	-	-	-	
Copper corrosion	Degree of corrosion	1 – 100 A 3					DIN EN ISO 2160
Steel corrosion							DIN ISO 7120
- 0-A: distilled water	Degree of corrosion	Pass					
- 0-B: salt water		Pass					
Scuffing and scoring test, FZG A/8.3/90	failure load stage	-	-	-	-	11	DIN ISO 14635-1
Brugger-Test	N/mm ²	30					DIN 51347-2
ISO filtrability dry / wet	-	Pass / pass					E DIN ISO 13357
Test electr. conductivity	-	conductivity high					Fuchs test procedure

CHARACTERISTICS: RENOLIN B RANGE (Continued)

RENOLIN		B 11 VG 37	B 15 VG 46	B 20 VG 68	B 30 VG 100	B 40 VG 150	B 50 VG 220	
Characteristics	Unit							Test Method
ISO VG		-	46	68	100	150	220	DIN 51519
Kinematic viscosity								DIN EN ISO 3104
at 40°C	mm ² /s	37	46	68	100	150.0	220	
at 100°C	mm ² /s	6.2	6.9	8.8	11.1	14.5	19.2	
Viscosity Index		103	105	100	96	94	97	DIN ISO 2909
Density at 15°C	kg/m ³	875	875	881	883	887	894	DIN 51757
Colour	ASTM	-	1.5	2.0	2.0	2.5	-	DIN ISO 2049
Flashpoint (Cleveland Open Cup)	°C	208	210	224	232	224	230	DIN ISO 2592
Auto-ignition temperature		-	350	360	370	380	-	DIN 51794
Pour point	°C	-31	-24	-24	-18	-15	-15	DIN ISO 3016
Neutralisation number	mg KOH/g	0.5	0.5	0.5	0.5	0.5	0.5	DIN 51558-3
Air release at 50°C (max.)	minutes	5	6	13	17	30	-	DIN ISO 9120
Demulsification								DIN ISO 6614
at 54°C	minutes	10	10	15	-	-	-	
at 82°C	minutes	-	-	-	5	5	-	
Copper corrosion	Degree of corrosion	1 – 100 A 3						DIN EN ISO 2160
Steel corrosion								DIN ISO 7120
- 0-A: distilled water	Degree of corrosion	Pass						
- 0-B: salt water		Pass						
Scuffing and scoring test, FZG A/8.3/90	failure load stage	-	11	11	11	11	-	DIN ISO 14635-1
Brugger-Test	N/mm ²	30						DIN 51347-2
ISO filtrability dry / wet	-	Pass / pass						E DIN ISO 13357
Test electr. conductivity)	-	conductivity high						Fuchs test procedure

WARNING: Never mix zinc-free hydraulic fluids with those containing zinc-based additives.