

RENOLIN THERM 330 S Synthetic Heat Transfer Fluid

Description

RENOLIN THERM 330 S is a synthetic heat transfer oil based on temperature-stable alkylbenzene for use in closed heat transfer systems. Selected additives improve the temperature and oxidation stability. The additives used in RENOLIN THERM 330 S also protect the system components from corrosion.

Application

RENOLIN THERM 330 S is optimal suited for use in the indirect heating of reactors, polymerization and distillation systems, processing machines and driers, as well as heat exchangers in processing systems, and in systems for heat recovery.

The heat transfer fluid is best used at temperatures ranging from 230 to 290 °C. The upper limit for use is an inlet temperature of 300 °C.

The film temperature should not exceed 320 °C.

Specifications

Heat transfer oil Q according to DIN 51522.

Advantages

- **High thermal stability**
- **Extremely low coking**
- **Wide application range**
- **Low residue formation, clean systems**
- **Selected synthetic components (narrow boiling range)**
- **Long service life**
- **Protects against corrosion**
- **Maximum film temperature: 320 °C**
- **Pumpable to – 7 °C**

RENOLIN THERM 330 S Synthetic Heat Transfer Fluid

Typical chemical and physical properties:

Product name	RENOLIN THERM 330 S		
Properties	Unit		Test method
Initial boiling point at 1013 mbar	°C	320	ASTM D 1078
Pourpoint	°C	-60	DIN ISO 3016
Density at 15 °C	kg/m ³	864	DIN 51757
Kinematic viscosity at 40 °C	mm ² /s	21	DIN EN ISO 3104
Flash point	°C	> 190	DIN ISO 2592
Ignition temperature	°C	357	DIN 51794
Permissible inlet temperature	°C	300	-
Maximum film temperature	°C	320	-
Pumpability limit	°C	- 7	-

PI 4-1144, Page 2; PM 4 / 01.17

FUCHS LUBRICANTS (UK) PLC
New Century Street, Hanley
GB-Stoke-on-Trent, Staffordshire, ST1 5HU

Tel +44-1782 -20 37 00
Fax +44-1782 -20 20 73
contact-uk@fuchs-oil.com



Health, Safety and Environment - information is provided for products in the relevant Safety Data Sheet. This provides guidance on potential hazards, precautions and first-aid measures, together with environmental effects and disposal of used products.

While the information and figures given here are typical of current production and conform to specification, minor variations may occur. No warranty expressed or implied is given concerning the accuracy of the information or the suitability of the products

RENOLIN THERM 330 S Synthetic Heat Transfer Fluid

Typical physical properties of RENOLIN THERM 330 S:

Temperature °C	Density kg/m ³	Specific heat kJ/kgK	Thermal conductivity W/m K	Kinematic viscosity mm ² /s	Vapour pressure mbar
-20	884	1.65	0.131	1322	
0	872	1.71	0.130	204	
20	861	1.79	0.129	54	
40	850	1.87	0.127	21	
60	839	1.94	0.126	11	
80	827	2.01	0.124	6	0.1
100	816	2.10	0.123	4.1	0.2
120	805	2.16	0.122	2.9	0.4
140	793	2.23	0.120	2.1	0.9
160	782	2.30	0.119	1.7	1.9
180	771	2.38	0.117	1.3	4.0
200	760	2.50	0.116	1.1	8.3
220	748	2.52	0.115	0.94	19.3
240	737	2.60	0.113	0.81	42.3
260	726	2.67	0.112	0.71	92.6
280	714	2.74	0.110	0.63	203
300	703	2.80	0.109	0.57	443
320	692	2.89	0.108	0.52	970